

ISOLDYN® -12000

Grey

Static load: up to N/mm² 12.000 Dynamic load: up to N/mm² 16.000

Load peaks: up to N/mm² 24.000

ISOLDYN® - 12000 Polyurethane foam mats

Closed cellular polyether-urethane mats for structure-borne sound insulation and vibration protection

Specification

- Does not absorb water
- Low natural frequency
- High insulating effect with shocks / vibrations

HBT-ISOL

- · Low dynamic stiffening factor
- · Constant characteristic values over a long service life
- Resistant to concrete grouts, oils, diluted acids and alkalis

Product- / Logistics data Thickness mm 6, 12.5 and 25 Stockholding Store in a dry place, do not expose to direct sunlight Length x width mm 2'000 x 500 Storage period Unlimited with correct storage

Technical data				
Size	Unit	Value	Test method	Comment
Mechanical loss factor		0.11	DIN 53513*	Guid value
Static E-modulus	N/mm ²	140	DIN 53513*	Compression: 12.000 N/mm ²
Dynamic sher modulus at 10 Hz	N/mm ²	370	DIN 53513*	Compression: 12.000 N/mm ²
Compression hardness	N/mm ²	9.0		at 10% deformation
Coefficient of friction with steel μ_s		0.5		Dry
Coefficient of friction with concrete μ_s		0.7		Dry
Inflammability		E	EN 13501-1	Normal flammable
Long-term temperature resistance	°C	Long-term: -30 to +70 Short-term: to +120		

* Measurement based on the corresponding standard.

Installation

Surface	Avoid direct contact between ISOLDYN [®] mats and materials containing plasticiser (use a release layer). Requirements storage area: Load capacity > dynamic load. No loose parts. Power troweled. Free from teeth and gravel nets. Flatness under 2-m-lath \leq 10 mm, > 10 mm re-profiling. Clean swept (Standard SIA-271:2007)
Installation	The connection points are fully pushed. Before applying the concrete, the ISOLDYN [®] mats are protected with a 2-ply tough PE foil (0.2 mm) and the overlap trapped to avoid cement contamination.
Screed requirement	Concrete or underlay flooring with flowable consistency as well as aerated concrete are only suitable to a limited extent and require additional, special sealing measures.
Processing instructions	The installation of ISOLDYN [®] mats should only be carried out by trained personnel. When using auxiliary products, e.g. adhesives, the ambient temperature and humidity must meet the requirements of the auxiliary products used. The corresponding product data sheets are to be considered.
Water	ISOLDYN [®] mats do not absorb moisture. As a result, the full structure-borne sound insulation is maintained even when in contact with water the shell construction phase and in the final state.

Safety- and Health instructions

Safety note	The local safty requirements must be considered
Transportation	The ISOLDYN [®] mats are not classified as "endangered products".
Disposal	Waste code according to European Waste Cataloge Ordinance: 07 02 13. Local requirements must be considered.

2.0

0

0

2

Deflection ∆h in mm

3

4

5

6

7



ISOLDYN[®] - 12000 Polyurethane foam mats

Important physical properties for dimensioning



Spring characteristic curve. Test speed v = 1 % of thickness. Test at room temperature between flat steel plates. Recording of the 3rd load. Form factor q = 2.

bis 24.0 N/mm²

Ą

Rare

load range

8

load peaks





Natural frequency of a system consisting of a rigid mass and a layer of ISOLDYN® on a rigid base. Form factor q = 2.

Load dependence of the static and dynamic moduli of elasticity. Dynamic E-modulus: harmonic excitation with an amplitude of \pm 0.11 mm at 10 Hz.

Static E-modulus: tangent modulus from the spring characteristic. Measurement according to DIN 53513. Form factor q = 2.

All informations and datas are based on our current knowledge and can be used as calculation or guideline values. These are dependent on manufacturing tolerances and do not constitute guaranteed properties. Changes reserved. Further technical information can be found on our website www.hbt-isol.com.